

Technical Data Sheet  
**IPETHENE® 111**  
 Low Density Polyethylene



**Product Description**

**IPETHENE® 111** is a low-density polyethylene film grade, produced by high-pressure autoclave technology.

<b>Features:</b>	<ul style="list-style-type: none"> <li>No additives</li> <li>Excellent bubble stability</li> <li>Good mechanical properties</li> </ul>	<ul style="list-style-type: none"> <li>Good processability</li> <li>Good optical properties</li> </ul>
<b>Uses:</b>	<ul style="list-style-type: none"> <li>Medium duty bags</li> <li>Agricultural films</li> <li>Multilayer and lamination films</li> </ul>	<ul style="list-style-type: none"> <li>Squeezable bottles</li> <li>Liners</li> <li>Pouches</li> <li>Shrink films</li> </ul>
<b>Processing Method:</b>	<ul style="list-style-type: none"> <li>Blown film extrusion</li> <li>Blow Molding</li> </ul>	

Properties		Method	Typical Value*	Unit
<b>Physical</b>				
<b>Melt Flow Rate</b>	(190°C/2.16 kg)	ISO 1133	0.7	g/10 min
<b>Density</b>		ISO 1183-A	0.920	g/cm <sup>3</sup>
<b>Thermal</b>				
<b>Peak Melting Temperature</b>	By DSC	ISO 11357-3	109	°C
<b>Vicat Softening Temperature</b>	(10 N)	ISO 306	95	°C
<b>Mechanical**</b>				
<b>Dart Drop Impact</b>	(F <sub>50</sub> )	ISO 7765-A	280	g
<b>Tensile Stress at Break</b>	(MD/TD)	ISO 527-3	27/25	MPa
<b>Tensile Strain at Break</b>	(MD/TD)	ISO 527-3	450/700	%
<b>Elmendorf Tear Strength</b>	(MD/TD)	ISO 6383-2	350/250	g
<b>Optical**</b>				
<b>Haze</b>		ASTM D 1003	7	%
<b>Gloss</b>	(45°)	ASTM D 2457	70	%

\*Typical values; not to be construed as specifications.

\*\* Measured on 50 µm blown film, Blow-up ratio 2.5:1, output 10 kg/h, melt temperature ~180°C.

**Processing Recommendations**

IPETHENE® 111 can be easily processed on conventional extruders at melt temperature range 160-180°C. Due to differences in screw and die head designs, processing conditions should be optimized for each production line. With suitable equipment, it can be drawn down to 25 µm films.

**Health, Quality, Regulations and Safety**

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.

Carmel Olefins Ltd. POB 1468 Haifa 31014 Israel  
 Website: <http://www.Carmel-Olefins.co.il>  
 Email: [techserv@caol.co.il](mailto:techserv@caol.co.il)

**Last updated: June 2017**

The information contained herein is to our knowledge accurate and reliable as of the date of publication. Carmel Olefins extends no warranties and makes no representations as to the accuracy or completeness of the information contained herein and assumes no responsibility regarding the consequences of its use or for any printing errors. Our products are intended for sale to industrial and commercial customers. It is the customer's responsibility to inspect and test our products in order to satisfy himself as to the suitability of the products for the customer's particular purpose. The customer is also responsible for the appropriate, safe and legal use, processing and handling of our products.